


## TEST REPORT

Test Report # 22B-000265 Date of Report Issue: March 2, 2022  
Date of Sample Received: February 21, 2022 Pages: Page 1 of 13

### CLIENT INFORMATION:

Company: Inkcups Now Corp.  
Recipient: Joe Shairs  
Recipient Email: joes@inkcups.com



### SAMPLE INFORMATION:


Description: CG Series Inks  
Assortment: - Purchase Order Number: -  
SKU/style No.: 122, 132, 121, 77RE, 131, 133, 111, 75RE, 79050, 141, 165, 110, 76RE, 160, 112, 130, 151 Toy Co./Agency: -  
Factory/Supplier/Vendor: - Country of Origin: -  
Country of Distribution: - Labeled Age Grade: -  
Quantity Submitted: 17 Recommended Age Grade: -  
Testing Period: 2/22/22 – 3/2/22 Tested Age Grade: -

### OVERALL RESULT:

 **PASS**

Refer to page 2 for test result summary and appropriate notes.

QIMA (US), LLC



Edward Nagel  
Manager, Laboratory Operations

**TEST RESULT SUMMARY:**

At the request of the client, the following tests were conducted:

CONCLUSION	TEST(S) CONDUCTED
PASS	CPSIA Section 101 & 16 CFR 1303, Total Lead Content in Paints & Surface Coatings
PASS	CPSIA Section 106 & ASTM F963-17 Section 4.3.5.1(2), Soluble Heavy Metals Content in Paints & Surface Coatings
PASS	ASTM F2923-20 Clause 5 & 8, Total Lead and Soluble Elements in Paint and Surface Coatings
PASS	The Illinois Lead Poisoning Prevention Act (LPPA) (410 ILCS 45/6), Total Lead Content in Surface Coatings of Children’s Jewelry and Childcare Articles
PASS	Connecticut Public Act 10-113 (Substituted House Bill 5314), Total Cadmium Content in Children’s Jewelry
PASS	Minnesota Chapter 347-S.F. No. 2510, Cadmium in Children's Jewelry
PASS	Maryland Chapter 578 (House Bill 145), Total Cadmium in Children’s Jewelry
PASS	Washington Children's Safe Products Act RCW 70.240.020, Cadmium Content
PASS	Canadian Surface Coating Materials Regulations SOR/2016-193, Total Lead and Mercury in Surface Coatings
PASS	Canadian Toys Regulations SOR/2011-17 amended by SOR/2016-195 & SOR/2016-302, Section 23, Total Lead, Total Mercury and Leachable Metals in Surface Coatings
PASS	Mexican Environmental Health NOM-252-SSA1-2011, Soluble Elements from Toys and School Supplies
PASS	16 CFR 1307 Prohibition of Children’s Toys and Child Care Articles Containing Specified Phthalates (8)
PASS	ASTM F2923-20 Clause 11, Phthalates in Plasticized Components of Children’s Jewelry
PASS	Client Requirement, California Proposition 65, Phthalate Content (6)
PASS	Revised Code of Washington Section 70.240.020, Phthalates in Children’s Product

**DETAILED RESULTS:**

**CPSIA Section 101 & 16 CFR 1303, Total Lead Content in Paints & Surface Coatings**  
**CPSIA Section 106 & ASTM F963-17 Section 4.3.5.1(2), Soluble Heavy Metals Content in Paints & Surface Coatings**  
**ASTM F2923-20 Clause 5 & 8, Total Lead and Soluble Elements in Paint and Surface Coatings**  
**Connecticut Public Act 10-113 (Substituted House Bill 5314), Total Cadmium Content in Children’s Jewelry**  
**The Illinois Lead Poisoning Prevention Act (LPPA) (410 ILCS 45/6), Total Lead Content in Surface Coatings of Children’s Jewelry and Childcare Articles**  
**Minnesota Chapter 347-S.F. No. 2510, Cadmium in Children’s Jewelry**  
**Maryland Chapter 578 (House Bill 145), Total Cadmium in Children’s Jewelry**  
**Washington Children’s Safe Products Act RCW 70.240.020, Cadmium Content**

Analytical determination by ICP-OES (Method: CPSC-CH-E1003-09.1)

	Specimen No.						
	1+2+3*	4+5+6*	7+8+9*	10+11+12*	13+14+15*		
	Total Result	Total Result	Total Result	Total Result	Total Result		
Lead (Pb)	LT 7	LT 6	LT 5	LT 6	LT 26	<b>CPSIA Total Limit</b>	
						90 ppm	
Lead (Pb)	LT 7	LT 6	LT 5	LT 6	LT 26	<b>ASTM F2923-20 Limit</b>	
						90 ppm	
Lead (Pb)	LT 7	LT 6	LT 5	LT 6	LT 26	<b>Illinois Total Limit</b>	
						40 ppm	
Cadmium (Cd)	LT 5	LT 5	LT 5	LT 5	LT 5	<b>Connecticut Total Limit</b>	
						75 ppm	
Cadmium (Cd)	LT 5	LT 5	LT 5	LT 5	LT 5	<b>Minnesota Total Limit</b>	
						75 ppm	
Cadmium (Cd)	LT 5	LT 5	LT 5	LT 5	LT 5	<b>Maryland Total Limit</b>	
						75 ppm	
Cadmium (Cd)	LT 5	LT 5	LT 5	LT 5	LT 5	<b>Washington Total Limit</b>	
						40 ppm	
	Total Result	Total Result	Total Result	Total Result	Total Result	<b>ASTM F963 Soluble Limits</b>	<b>ASTM F2923 Soluble Limits</b>
Antimony (Sb)	LT 5	LT 5	LT 5	LT 5	LT 5	60 ppm	60 ppm
Arsenic (As)	LT 5	LT 5	LT 5	LT 5	LT 5	25 ppm	25 ppm
Barium (Ba)	17	LT 5	LT 5	LT 5	LT 5	1000 ppm	1000 ppm
Cadmium (Cd)	LT 5	LT 5	LT 5	LT 5	LT 5	75 ppm	75 ppm
Chromium (Cr)	6	LT 5	17	LT 5	13	60 ppm	60 ppm
Lead (Pb)	LT 7	LT 6	LT 5	LT 6	LT 26	90 ppm	-
Mercury (Hg)	LT 5	LT 5	LT 5	LT 5	LT 5	60 ppm	60 ppm
Selenium (Se)	LT 6	LT 7	LT 5	LT 7	LT 5	500 ppm	500 ppm
<b>Conclusion</b>	PASS	PASS	PASS	PASS	PASS		

LT = Less Than

Results are reported in parts per million (ppm)

**Notes:** The total heavy metals results do not exceed the soluble heavy metals limits; therefore, further soluble analyses were not conducted.

\*Composited results are based on specimen of least mass resulting in highest potential concentration.

**DETAILED RESULTS:**

**CPSIA Section 101 & 16 CFR 1303, Total Lead Content in Paints & Surface Coatings**  
**CPSIA Section 106 & ASTM F963-17 Section 4.3.5.1(2), Soluble Heavy Metals Content in Paints & Surface Coatings**  
**ASTM F2923-20 Clause 5 & 8, Total Lead and Soluble Elements in Paint and Surface Coatings**  
**Connecticut Public Act 10-113 (Substituted House Bill 5314), Total Cadmium Content in Children’s Jewelry**  
**The Illinois Lead Poisoning Prevention Act (LPPA) (410 ILCS 45/6), Total Lead Content in Surface Coatings of Children’s Jewelry and Childcare Articles**  
**Minnesota Chapter 347-S.F. No. 2510, Cadmium in Children’s Jewelry**  
**Maryland Chapter 578 (House Bill 145), Total Cadmium in Children’s Jewelry**  
**Washington Children’s Safe Products Act RCW 70.240.020, Cadmium Content**

Analytical determination by ICP-OES (Method: CPSC-CH-E1003-09.1)

	Specimen No.						
	16+17*	-	-	-	-		
	Total Result	Total Result	Total Result	Total Result	Total Result		
Lead (Pb)	LT 5	-	-	-	-	<b>CPSIA Total Limit</b>	
						90 ppm	
Lead (Pb)	LT 5	-	-	-	-	<b>ASTM F2923-20 Limit</b>	
						90 ppm	
Lead (Pb)	LT 5	-	-	-	-	<b>Illinois Total Limit</b>	
						40 ppm	
Cadmium (Cd)	LT 5	-	-	-	-	<b>Connecticut Total Limit</b>	
						75 ppm	
Cadmium (Cd)	LT 5	-	-	-	-	<b>Minnesota Total Limit</b>	
						75 ppm	
Cadmium (Cd)	LT 5	-	-	-	-	<b>Maryland Total Limit</b>	
						75 ppm	
Cadmium (Cd)	LT 5	-	-	-	-	<b>Washington Total Limit</b>	
						40 ppm	
	Total Result	Total Result	Total Result	Total Result	Total Result	<b>ASTM F963 Soluble Limits</b>	<b>ASTM F2923 Soluble Limits</b>
Antimony (Sb)	LT 8	-	-	-	-	60 ppm	60 ppm
Arsenic (As)	LT 5	-	-	-	-	25 ppm	25 ppm
Barium (Ba)	420	-	-	-	-	1000 ppm	1000 ppm
Cadmium (Cd)	LT 5	-	-	-	-	75 ppm	75 ppm
Chromium (Cr)	LT 5	-	-	-	-	60 ppm	60 ppm
Lead (Pb)	LT 5	-	-	-	-	90 ppm	-
Mercury (Hg)	LT 5	-	-	-	-	60 ppm	60 ppm
Selenium (Se)	LT 6	-	-	-	-	500 ppm	500 ppm
<b>Conclusion</b>	PASS	-	-	-	-		

LT = Less Than

Results are reported in parts per million (ppm)

**Notes:** The total heavy metals results do not exceed the soluble heavy metals limits; therefore, further soluble analyses were not conducted.

\*Composited results are based on specimen of least mass resulting in highest potential concentration.

**DETAILED RESULTS:**

**Canadian Surface Coating Materials Regulations SOR/2016-193, Total Lead and Mercury in Surface Coatings**

Analytical determination by ICP-OES (Method: CPSC-CH-E1003-09.1)

	Specimen No.				Total Limits
	1+2+3*	4+5+6*	7+8+9*	10+11+12*	
	Total Result	Total Result	Total Result	Total Result	
Lead (Pb)	LT 7	LT 6	LT 5	LT 6	90 ppm
Mercury (Hg)	LT 5	LT 5	LT 5	LT 5	10 ppm
<b>Conclusion</b>	PASS	PASS	PASS	PASS	

	Specimen No.				Total Limits
	13+14+15*	16+17*	-	-	
	Total Result	Total Result	Total Result	Total Result	
Lead (Pb)	LT 26	LT 5	-	-	90 ppm
Mercury (Hg)	LT 5	LT 5	-	-	10 ppm
<b>Conclusion</b>	PASS	PASS	-	-	

LT = Less Than

Results are reported in parts per million (ppm)

**\*Note:** Compositd results are based on specimen of least mass resulting in highest potential concentration.

**DETAILED RESULTS:**

**Canadian Toys Regulations SOR/2011-17 as amended, Section 23, Total Lead, Total Mercury and Leachable Metals in Surface Coatings**

Analytical determination by ICP-OES (Method: CPSC-CH-E1003-09.1)

	Specimen No.						Total Limits
	1+2+3*	4+5+6*	7+8+9*	10+11+12*	13+14+15*	16+17*	
	Total Result	Total Result	Total Result	Total Result	Total Result	Total Result	
Lead (Pb)	LT 7	LT 6	LT 5	LT 6	LT 26	LT 5	90 ppm
Mercury (Hg)	LT 5	LT 5	LT 5	LT 5	LT 5	LT 5	10 ppm
	Total Result	Total Result	Total Result	Total Result	Total Result	Total Result	Leachable Limits
Antimony (Sb)	LT 5	LT 5	LT 5	LT 5	LT 5	LT 8	1000 ppm
Arsenic (As)	LT 5	LT 5	LT 5	LT 5	LT 5	LT 5	1000 ppm
Barium (Ba)	17	LT 5	LT 5	LT 5	LT 5	420	1000 ppm
Cadmium (Cd)	LT 5	LT 5	LT 5	LT 5	LT 5	LT 5	1000 ppm
Selenium (Se)	LT 6	LT 7	LT 5	LT 7	LT 5	LT 6	1000 ppm
<b>Conclusion</b>	PASS	PASS	PASS	PASS	PASS	PASS	

LT = Less Than

Results are reported in parts per million (ppm)

**Notes:** The total metal results do not exceed the leachable limits; therefore, leachable analyses were not conducted.

\*Composited results are based on specimen of least mass resulting in highest potential concentration.

**DETAILED RESULTS:**

**Mexican Environmental Health NOM-252-SSA1-2011, Soluble Elements from Toys and School Supplies**

Analytical determination by ICP-OES (Method: CPSC-CH-E1003-09.1)

	Specimen No.						Soluble Limits
	1+2+3*	4+5+6*	7+8+9*	10+11+12*	13+14+15*	16+17*	
	Total Result	Total Result	Total Result	Total Result	Total Result	Total Result	
Antimony (Sb)	LT 5	LT 5	LT 5	LT 5	LT 5	LT 8	60 ppm
Arsenic (As)	LT 5	LT 5	LT 5	LT 5	LT 5	LT 5	25 ppm
Barium (Ba)	17	LT 5	LT 5	LT 5	LT 5	420	1000 ppm
Cadmium (Cd)	LT 5	LT 5	LT 5	LT 5	LT 5	LT 5	75 ppm
Chromium (Cr)	6	LT 5	17	LT 5	13	LT 5	60 ppm
Lead (Pb)	LT 7	LT 6	LT 5	LT 6	LT 26	LT 5	90 ppm
Mercury (Hg)	LT 5	LT 5	LT 5	LT 5	LT 5	LT 5	60 ppm
Selenium (Se)	LT 6	LT 7	LT 5	LT 7	LT 5	LT 6	500 ppm
<b>Conclusion</b>	PASS	PASS	PASS	PASS	PASS	PASS	

LT = Less Than

Results are reported in parts per million (ppm)

**Notes:** The total heavy metals results do not exceed the soluble heavy metals limits; therefore, further soluble analyses were not conducted.

\*Composited results are based on specimen of least mass resulting in highest potential concentration.

**DETAILED RESULTS:**

**16 CFR 1307 Prohibition of Children’s Toys and Child Care Articles Containing Specified Phthalates (8)  
 ASTM F2923-20 Clause 11, Phthalates in Plasticized Components of Children’s Jewelry  
 Client Requirement, California Proposition 65, Phthalate Content (6)**

Analytical determination by GC/MS (Method: CPSC-CH-C1001-09.4)

Phthalate	Specimen No.				16 CFR 1307 & ASTM F2923 Limits (%)	Client Limits, Cal Prop (%)
	1+2+3*	4+5+6*	7+8+9*	10+11+12*		
dibutyl phthalate (DBP)	LT 0.01	LT 0.01	LT 0.01	LT 0.01	0.1	0.1
benzyl butyl phthalate (BBP)	LT 0.01	LT 0.01	LT 0.01	LT 0.01	0.1	0.1
di-(2-ethylhexyl) phthalate (DEHP)	LT 0.01	LT 0.01	LT 0.01	LT 0.01	0.1	0.1
diisononyl phthalate (DINP)	LT 0.02	LT 0.02	LT 0.02	LT 0.02	0.1	0.1
diisodecyl phthalate (DIDP)	LT 0.02	LT 0.02	LT 0.02	LT 0.02	-	0.1
di-n-hexyl phthalate (DnHP/DHEXP)	LT 0.01	LT 0.01	LT 0.01	LT 0.01	0.1	0.1
diisobutyl phthalate (DiBP)	LT 0.01	LT 0.01	LT 0.01	LT 0.01	0.1	-
di-n-pentyl phthalate (DnPP/DPENP)	LT 0.01	LT 0.01	LT 0.01	LT 0.01	0.1	-
dicyclohexyl phthalate (DCHP)	LT 0.01	LT 0.01	LT 0.01	LT 0.01	0.1	-
<b>Conclusion</b>	PASS	PASS	PASS	PASS		

LT = Less Than

Results reported as percent by weight

**\*Note:** Composited results are based on specimen of least mass resulting in highest potential concentration.



**DETAILED RESULTS:**

**16 CFR 1307 Prohibition of Children’s Toys and Child Care Articles Containing Specified Phthalates (8)  
ASTM F2923-20 Clause 11, Phthalates in Plasticized Components of Children’s Jewelry  
Client Requirement, California Proposition 65, Phthalate Content (6)**

Analytical determination by GC/MS (Method: CPSC-CH-C1001-09.4)

Phthalate	Specimen No.				16 CFR 1307 & ASTM F2923 Limits (%)	Client Limits, Cal Prop (%)
	13+14+15*	16+17*	-	-		
dibutyl phthalate (DBP)	LT 0.01	LT 0.01	-	-	0.1	0.1
benzyl butyl phthalate (BBP)	LT 0.01	LT 0.01	-	-	0.1	0.1
di-(2-ethylhexyl) phthalate (DEHP)	LT 0.01	LT 0.01	-	-	0.1	0.1
diisononyl phthalate (DINP)	LT 0.02	LT 0.02	-	-	0.1	0.1
diisodecyl phthalate (DIDP)	LT 0.02	LT 0.02	-	-	-	0.1
di-n-hexyl phthalate (DnHP/DHEXP)	LT 0.01	LT 0.01	-	-	0.1	0.1
diisobutyl phthalate (DiBP)	LT 0.01	LT 0.01	-	-	0.1	-
di-n-pentyl phthalate (DnPP/DPENP)	LT 0.01	LT 0.01	-	-	0.1	-
dicyclohexyl phthalate (DCHP)	LT 0.01	LT 0.01	-	-	0.1	-
<b>Conclusion</b>	PASS	PASS	-	-		

LT = Less Than

Results reported as percent by weight

**\*Note:** Composited results are based on specimen of least mass resulting in highest potential concentration.

**DETAILED RESULTS:**

**Revised Code of Washington Section 70.240.020, Phthalates in Children’s Product**

Analytical determination by GC/MS (Method: CPSC-CH-C1001-09.4)

Phthalate	Specimen No.					Limits (%)
	1+2+3*	4+5+6*	7+8+9*	10+11+12*	13+14+15*	
Dibutyl Phthalate (DBP)	LT 0.01	LT 0.01	LT 0.01	LT 0.01	LT 0.01	0.1
Benzyl Butyl Phthalate (BBP)	LT 0.01	LT 0.01	LT 0.01	LT 0.01	LT 0.01	0.1
Di-(2-ethylhexyl) Phthalate (DEHP)	LT 0.01	LT 0.01	LT 0.01	LT 0.01	LT 0.01	0.1
Di-n-octyl Phthalate (DnOP)	LT 0.01	LT 0.01	LT 0.01	LT 0.01	LT 0.01	0.1
Diisononyl Phthalate (DINP)	LT 0.02	LT 0.02	LT 0.02	LT 0.02	LT 0.02	0.1
Diisodecyl Phthalate (DIDP)	LT 0.02	LT 0.02	LT 0.02	LT 0.02	LT 0.02	0.1
Sum of Above (6)	LT 0.02	LT 0.02	LT 0.02	LT 0.02	LT 0.02	0.1
<b>Conclusion</b>	PASS	PASS	PASS	PASS	PASS	

LT = Less Than

Results reported as percent by weight

**\*Note:** Composited results are based on specimen of least mass resulting in highest potential concentration.

**DETAILED RESULTS:**

**Revised Code of Washington Section 70.240.020, Phthalates in Children’s Product**

Analytical determination by GC/MS (Method: CPSC-CH-C1001-09.4)

Phthalate	Specimen No.					Limits (%)
	16+17*	-	-	-	-	
Dibutyl Phthalate (DBP)	LT 0.01	-	-	-	-	0.1
Benzyl Butyl Phthalate (BBP)	LT 0.01	-	-	-	-	0.1
Di-(2-ethylhexyl) Phthalate (DEHP)	LT 0.01	-	-	-	-	0.1
Di-n-octyl Phthalate (DnOP)	LT 0.01	-	-	-	-	0.1
Diisononyl Phthalate (DINP)	LT 0.02	-	-	-	-	0.1
Diisodecyl Phthalate (DIDP)	LT 0.02	-	-	-	-	0.1
Sum of Above (6)	LT 0.02	-	-	-	-	0.1
<b>Conclusion</b>	PASS	-	-	-	-	

LT = Less Than

Results reported as percent by weight

**\*Note:** Composited results are based on specimen of least mass resulting in highest potential concentration.

**SPECIMEN DESCRIPTION:**

Specimen No.	Specimen Description (Color)	Location
1	Wet Ink - Blue	CG Series 132 - Blue
2	Wet Ink - Orange	CG Series 121 - Deep Orange
3	Wet Ink - Gold	CG Series 75RE - Golden
4	Wet Ink - Yellow	CG Series 112 - Yellow
5	Wet Ink - Green	CG Series 141 - Deep Green
6	Wet Ink - Blue	CG Series 133 - Deep Blue
7	Wet Ink - Black	CG Series 165 - Black
8	Wet Ink - Silver	CG Series 79050 - Silvery
9	Wet Ink - Yellow	CG Series 110 - Bright Yellow
10	Wet Ink - White	CG Series 160 - White
11	Wet Ink - Blue	CG Series 131 - Dull Blue
12	Wet Ink - Blue	CG Series 130 - Light Blue
13	Wet Ink - Yellow	CG Series 111 - Dull Yellow
14	Wet Ink - Gold	CG Series 76RE - Dull Golden
15	Wet Ink - Copper	CG Series 77RE - Coppery
16	Wet Ink - Brown	CG Series 151 - Brown
17	Wet Ink - Red	CG Series 122 - Red

**SAMPLE PHOTO:**



-End Report-